



"Your Source For Packaging, Shipping & Safety Supplies"
"Ship right with Wrap-Tite"



Air-Lite Blown Pre-Stretch Technical Data Sheet

- Pre-Stretch Blown Film with good tack and puncture resistance
- Re-inforced edges makes it nick proof
- Lightweight & ergonomic
- Reduces fatigue during application
- Product Categories – EWHF



Thickness	ASTM D-4649	Mic	7.4 mic
Tensile Ultimate MD	ASTM D-882	PSI	18000
Tensile Ultimate TD	ASTM D-882	PSI	3280
Tensile Yield MD	ASTM D-882	PSI	No Yield
Tensile Yield MD	ASTM D-882	PSI	1560
Elongation MD	ASTM D-882	%	80
Elongation TD	ASTM D-882	%	704
Elmendorf Tear MD	ASTM D-1922	g/mil	140
Elmendorf Tear TD	ASTM D-1922	g/mil	980
Cling	ASTM D-5458	g/in	150

- *All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*

Email: info@wraptite.com, **B2B:** www.wraptite.com

Head Quarters: 6200 Cochran Road, Solon, Ohio 44139

Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/

Manufacturing: 6075 Cochran Road, Solon, Ohio 44139

Fax: 440-349-5432