



"Your Source For Packaging, Shipping & Safety Supplies"
"Ship right with Wrap-Tite"



Anti-Stat specs for all Cast Hand and Machine film

- Applicable to all Machine and Hand films with Anti Stat additive (Part no's starting with ZMA, ZHA, CMA, CHA & Any other Anti Stat films)
- Static Dissipative Range is 10^5 - 10^{12} , Insulative Range is $> 10^{12}$



Surface Resistivity as Made:	ASTM D527	3.30×10^{16}
Surface Resistivity 2 Days:	ASTM D527	3.30×10^{16}
Surface Resistivity 10 Days:	ASTM D527	3.43×10^{13}
Surface Resistivity 21 Days:	ASTM D527	3.76×10^{12}
Surface Resistivity 40 Days:	ASTM D527	3.27×10^{12}

All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.

Email: info@wraptite.com, **B2B:** www.wraptite.com
Head Quarters: 6200 Cochran Road, Solon, Ohio 44139
Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/
Manufacturing: 6075 Cochran Road, Solon, Ohio 44139
Fax: 440-349-5432