



"Your Source For Packaging, Shipping & Safety Supplies"
"Ship right with Wrap-Tite"



Blown Hand Film Technical Data Sheet

- Puncture Resistant
- Excellent Cling
- Self-Clinging without residue
- Resists tearing at sharp corners
- Works at low temperatures
- Product Categories – BHF



Thickness	ASTM D-4649	Gauge	70 ga	75 ga	80 ga	90 ga	100 ga	120 ga
Tensile Ultimate MD	ASTM D-882	PSI	6900	6900	6800	6700	6600	6500
Tensile Ultimate TD	ASTM D-882	PSI	4700	4700	4600	4500	4300	4400
Tensile Yield MD	ASTM D-882	PSI	1600	1600	1600	1600	1600	1700
Tensile Yield TD	ASTM D-882	PSI	1700	1700	1700	1700	1700	1800
Elongation MD	ASTM D-882	%	410	470	470	465	530	600
Elongation TD	ASTM D-882	%	680	700	720	750	720	850
Elmendorf Tear MD	ASTM D-1922	g/mil	160	140	150	150	120	130
Elmendorf Tear TD	ASTM D-1922	g/mil	500	750	500	500	750	700
Cling@100%	ASTM D-5458	g/in	150	150	150	150	150	150

- *All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*

Email: info@wraptite.com, B2B: www.wraptite.com

Head Quarters: 6200 Cochran Road, Solon, Ohio 44139

Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/

Manufacturing: 6075 Cochran Road, Solon, Ohio 44139

Fax: 440-349-5432