



"Your Source For Packaging, Shipping & Safety Supplies"
"Ship right with Wrap-Tite"



Blown Machine Film Technical Data Sheet

- Puncture resistant
- Stretches 200-250%
- Excellent cling & works at low temperatures
- Resists tearing at sharp corners
- Product Categories – BMF



Thickness	ASTM D-4649	Gauge	80 ga	90 ga	120 ga
Tensile Ultimate MD	ASTM D-882	PSI	6900	6900	6800
Tensile Ultimate TD	ASTM D-882	PSI	4900	4900	4900
Tensile Yield MD	ASTM D-882	PSI	1600	1600	1600
Tensile Yield TD	ASTM D-882	PSI	1700	1700	1500
Elongation MD	ASTM D-882	%	550	550	600
Elongation TD	ASTM D-882	%	750	750	800
Elmendorf Tear MD	ASTM D-1922	g/mil	150	150	150
Elmendorf Tear TD	ASTM D-1922	g/mil	750	750	750
Cling@100%	ASTM D-5458	g/in	150	150	150

- *All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*

Email: info@wraptite.com, **B2B:** www.wraptite.com

Head Quarters: 6200 Cochran Road, Solon, Ohio 44139

Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/

Manufacturing: 6075 Cochran Road, Solon, Ohio 44139

Fax: 440-349-5432