



"Your Source For Packaging, Shipping & Safety Supplies"
"Ship right with Wrap-Tite"



Performance Machine Film Technical Data Sheet



- Easy release and one side cling film
- Stretches up to 300%
- Replaces thicker film for a lower per unit cost
- Great load containment
- Available in various colors (Dark & Tinted) in certain gauges – Black, Blue, Green, Red, Orange, Yellow, Purple, White (Custom Colors are available up on request)
- Product Categories – PMF, ZPMF and Printed machine films

Thickness	ASTM D-4649	Gauge	47 ga	51 ga	55 ga	63 ga	70 ga	80 ga	90 ga	100 ga
Tensile Ultimate MD	ASTM D-882	PSI	6620	6620	6620	6620	6670	6670	6670	6670
Tensile Ultimate TD	ASTM D-882	PSI	5470	5470	5470	5470	5520	5520	5520	5520
Tensile Yield MD	ASTM D-882	PSI	1370	1370	1370	1370	1320	1320	1320	1320
Tensile Yield TD	ASTM D-882	PSI	1270	1270	1270	1270	1220	1220	1220	1220
Elongation MD	ASTM D-882	%	450	450	480	480	510	510	540	540
Elongation TD	ASTM D-882	%	690	690	710	710	720	720	730	730
Elmendorf Tear MD	ASTM D-1922	g/mil	310	310	310	310	310	310	310	310
Elmendorf Tear TD	ASTM D-1922	g/mil	510	510	510	510	510	510	510	510
Puncture Force	WRAP TITE	LBS	6.2	6.5	7.1	7.8	8.6	10	10.3	10.7
Cling@200%	ASTM D-5458	g/in	150	150	150	150	150	150	150	150

- *All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.*

Email: info@wraptite.com, **B2B:** www.wraptite.com

Head Quarters: 6200 Cochran Road, Solon, Ohio 44139

Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/

Manufacturing: 6075 Cochran Road, Solon, Ohio 44139

Fax: 440-349-5432